

Fiber stress of typical pole species¹

		psi
Cedar, western red	Thuja plicata	6000
Pine, jack	Pinus banksiana	6600
Pine, lodgepole	Pinus contorta	6600
Pine, ponderosa	Pinus ponderosa	6000
Pine, red	Pinus resinosa	6600
Pine, southern		
Loblolly	Pinus taeda	8000
Longleaf	Pinus palustris	8000
Shortleaf	Pinus echinata	8000
Slash	Pinus elliotii	8000

¹per ANSI 05.1 - 1992 based on kiln drying