



## FIRE RETARDANT TREATED TIMBER AND SHEET MATERIALS CODE OF PRACTICE

Helping you make the most of timber

### GUIDANCE FOR USE

This document is designed to assist those using or specifying NON-COM EXTERIOR treated materials. The Code of Practice gives guidance prior to treatment and supplies information on ancillary properties and post-treatment use. Consult the Arch Specifier's Guide to NON-COM EXTERIOR fire retardant treated timber for general information.

### DESCRIPTION

NON-COM EXTERIOR fire retardant treated timber and sheet materials have been impregnated with NON-COM EXTERIOR fire retardant under controlled conditions in vacuum pressure timber impregnation plant. It is then kiln dried before being subjected to a high temperature curing process, converting water soluble chemicals to a permanently bonded water insoluble resin.

NON-COM EXTERIOR fire retardant is an advanced polymer based formulation, free from halogenated compounds. It is the only listed status type LR (Leach Resistant) treatment in the UK Wood Protection Association (WPA) Manual and is classified as suitable for exterior use (EXT class) under prEN 15912 – the draft European Standard on fire retardant durability.

### TYPICAL APPLICATIONS

NON-COM EXTERIOR treated materials are designed to be used in exterior or severe damp situations without the need for further protection. Typical applications include exterior cladding, exposed timbers and cedar shingles and shakes. This list is not totally exhaustive and gives an indication of the range of uses for NON-COM EXTERIOR treated materials.

It is advisable to consult with Arch Timber Protection using the contact details given in this document if in doubt about any particular area of application or compliance with other relevant standards or specifications.

### BEFORE TREATMENT

A wide range of timber based materials can be treated with NON-COM EXTERIOR. Always obtain full details of where and how the timber will be used before treatment and then discuss your requirements with Arch Timber Protection to confirm relevant test data and classification reports are available.

**The responsibility for determining that any product or building component complies with the relevant Building Regulations or Codes of Practice rests solely with the client or specifier.**

To help define the relevant project specific standards and requirements, consult the Arch Specifier's Guide to NON-COM EXTERIOR fire retardant treated timber, which also gives guidance on recommended wording of specifications. Full assistance with specification writing is available on request.



## PREPARATION OF TIMBER FOR TREATMENT

The quality and appearance of the end-product is dependent on the quality and appearance of the substrate prior to processing. Timber and plywood should be presented to the treatment centre in a dry and clean condition as follows:

- Timber boarding must be dried to a moisture content of 22% or less, and preferably to its end use moisture content.
- Large cross sectional timber must have a moisture content of 28% or less, and preferably to its end use moisture content.
- All inner and outer bark must be removed from solid timber prior to treatment.
- Material should be free from dirt, sawdust, surface coatings, surface water, plastic wrapping, ice and snow.
- Material should be free from all signs of attack by bacteria, blue staining fungi, wood destroying fungi or insect.
- As far as possible, all ripping, profiling, notching, boring and extensive machining should be completed before treatment. See section on post-treatment machining.
- Timber and plywood must be adequately sheeted at all times during transport to and from the treatment plant and on-site.
- Packs must be adequately banded (not too tight) to avoid degradation during transport and handling and to allow good penetration during treatment. For maximum length and relevant pack size, please contact Arch Timber Protection.
- Supply a minimum 5% extra material with each order to allow for kiln degrade, kiln samples and moisture content samples. Some species will require more of a wastage factor than others. Consult Arch for further advice.

The final moisture content of NON-COM EXTERIOR treated timber is in the region of 15-18%. This should be taken into account if supplying profiled components machined at moisture contents above this figure. For close tolerance work all timber must be machined at its equilibrium service moisture content.

It is advisable to have representative samples treated prior to carrying out full scale treatments. The client can then be assured of the acceptability of the treated product.

## TREATMENT OF PRE-GLUED ASSEMBLIES

In general, glued assemblies can be safely treated through the NON-COM EXTERIOR process, provided suitable waterproof adhesives have been used. Always consult the adhesive manufacturer on the suitability and use of their particular product and follow the directions of the appropriate regional standards.

The adhesive must be allowed time to gain sufficient strength to tolerate the effect of the vacuum pressure treatment.


If plywood is required, BS EN 636 Exterior grade (BS EN 314 Part 2 bonding class 3) should be specified.

Under previous systems, plywood was graded WBP (Weather and Boil Proof) under BS1204. This standard has now been withdrawn. Now plywood grades are based on BS EN 636 (Dry, Humid and Exterior classifications), which themselves are based on bonding classes 1, 2 and 3 from BS EN 314 Part 2. Plywood that is BS EN 636 Exterior grade (BS EN 314 Part 2 bonding class 3) should now be specified. Humid grade (bonding class 2) might be acceptable, but the board manufacturer or supplier should be asked to confirm that Humid grade board can be put through a high vacuum-pressure treatment process. Delamination can occur with plywood of grading other than Exterior.

It is recommended that advice be sought before sending any material for treatment.

## APPEARANCE

The appearance of timber is commonly not significantly affected by NON-COM EXTERIOR treatment. However under certain conditions, treatment may darken the wood slightly, dependent on species, but the basic tone and hue of the wood generally remains unchanged.



For decorative solid timbers the use of less resinous timbers such as Western Red Cedar and Siberian Larch is recommended. With the use of Redwood (*Pinus sylvestris*) there is the possibility of natural resin exudation being accentuated by the heat curing process. To a lesser extent, resin exudation may occur with Douglas Fir.

The treatment process can generate splitting, cracking, cupping, or bowing of certain materials. Movements are dependent on species and commodities.

Sticker marks can occur as a result of the treatment. When material is to be used decoratively, if specified and where possible, it will be dried with a sticker mark free face for an architectural finish.

For pre-glued material, any weaknesses in the glueline may be exaggerated as a result of treatment. This is most noticeable where uneven glue is spread or pre-curing has occurred in manufacture.

## **CONFIRMATION OF TREATMENT**

NON-COM EXTERIOR treatments are carried out in accordance with the WPA Quality Scheme operating under ISO 9001 Quality and ISO 14001 Environmental standards.

Full details of the NON-COM EXTERIOR treatment process are recorded for each charge. This ensures that the treatment conforms to the specification and that the correct treatment process and kiln drying schedule has been followed. A Treatment Certificate will be issued on request.

Please note that the treatment process parameters are varied according to the timber species and end use of the treated material commodity, taking into account the required fire performance.

## **POST TREATMENT STORAGE**

Before and after processing, the timbers and plywood must be protected from the weather during storage.

NON-COM EXTERIOR processed material, being kiln dried, will reach the building site at a pre-specified moisture content and is ready for immediate installation. If the treated material is to be stored on-site prior to installation, this should be in a building with atmospheric conditions corresponding to its service environment.

If storage in a building is not possible, the treated material must be stored out of ground contact and well protected from the ingress of moisture and dirt by a protective covering e.g. a tarpaulin or plastic sheeting, whilst allowing the treated material to breathe.

NON-COM EXTERIOR treated materials are valuable building products and should be stored with care at all times to avoid physical damage and surface disfiguration.

## **POST TREATMENT MACHINING**

As far as possible all cutting, machining, notching and boring is to be carried out prior to treatment.

Fire classification applies to the final form of a material. The fire performance of any rip sawn, thickened, equalised or planed material will be downgraded. The machined material must be returned to the plant for re-treatment with NON-COM EXTERIOR.

## **POST TREATMENT GLUING**

It is the end user's responsibility to ensure compatibility of any adhesive to be used. When NON-COM EXTERIOR treated material is to be bonded, always consult the adhesive manufacturer for suitable recommendations.

In consultation with the adhesive manufacturer, select an adhesive appropriate to the in-service exposure conditions and the load bearing or non-load bearing requirements. The adhesive manufacturer should also inform you on the suitability and use of their particular product and give guidelines to follow the directions of the appropriate regional standards.

Prior to bonding, a preparation of the material might be required. Always consult your adhesive manufacturer for appropriate recommendations on surface preparation and specifications during bonding. For your information, the curing time and temperature during bonding might have to be increased.

## **SURFACE COATINGS**

Because NON-COM EXTERIOR treated timber is specifically designed for external situations, a decorative finish is not required. However, when it is preferred, NON-COM EXTERIOR treated materials have been successfully coated with clear, pigmented and opaque products.

It is the end users responsibility to ensure compatibility of any coating to be used. When NON-COM EXTERIOR treated material is to be coated, always consult the coating manufacturer for suitable recommendations, and confirmation of adhesion and long term durability characteristics. Coated surfaces will require maintenance in accordance with the manufacturer's instructions.

When painting or staining, as with untreated timber, the surface should be clean and dry throughout the surface. A light sanding and thorough wiping with a damp cloth, or power washing should be performed prior to the application of any finish to provide a clean surface and to smooth any raised grain to optimise adhesion. In the case of rough sawn timber or textured plywood, brush the surface prior to staining.

As with untreated wood, excessive surface moisture can cause finishing problems. The timber surface should be dried to an appropriate moisture content prior to finishing. If coating is to be undertaken on site, it is important to take appropriate precautions to protect the treated product from exposure to rain or extreme dampness.

The paint or stain manufacturer's recommendations should be followed taking note of the recommended maximum moisture content. The recommendations on sound painting practices, which are detailed in BS6150 - Code of Practice for the Painting of Buildings - should be followed.

It is important to confirm the final finish does not downgrade fire performance, achieved by the NON-COM EXTERIOR treatment. Highly flammable finishes such as nitro-cellulose based lacquers must not be used.

Always consult your coating manufacturer before applying a coating product to NON-COM EXTERIOR treated material.

## **METAL FIXINGS AND FITTINGS**

It is important to follow the recommendations of the manufacturer of any metal products used for specific advice regarding suitability, desired service life expectations and particular exposure conditions. Hot-dipped galvanised or stainless steel fixings and fasteners are recommended.

NON-COM EXTERIOR pressure treated timber has a long life expectancy and it is appropriate to use metal fixings and fastenings that will have a comparable length of life.

- Performance of metal fixings is influenced by the environmental conditions including moisture content, temperature, atmospheric pollution, proximity to coastal locations, timber species, as well as the thickness of any galvanising.
- Galvanising provides a sacrificial zinc barrier. It is important that the specifier is aware that there are many thicknesses of galvanised coating available and the thicker the galvanised coating the longer the expected service life. The level of galvanising should be commensurate with the end use.
- For exterior use, where the timber is likely to become wet and a long service life is required, greater corrosion resistance will be achieved with use of stainless steel in preference to other types of fittings.
- Electroplated metals only provide a thin coating and are unsuitable for exterior applications.
- Due to a high level of tannic acid, species such as western red cedar or oak can cause corrosion to unprotected metals. For these species, it is therefore recommended to use galvanised or stainless steel.
- To prevent bimetallic corrosion between fastener/connector components it is important not to mix metals in the same connection. DO NOT mix galvanised and stainless steel components.
- Attach connectors/fasteners/fittings after treatment and when moisture content is less than 20%.
- Fixings and fastenings used on safety critical and load bearing components should be inspected regularly and replaced if necessary.
- It is good practice to drill pilot holes for fixings, in particular when screwing near the edge or end of a piece of timber.

## **DURABILITY OF FIRE PERFORMANCE**

The heat curing process involved in the NON-COM EXTERIOR treatment polymerises the organic resins to form insoluble polymer molecules, locked inside the timber cells. The leach resistance of NON-COM EXTERIOR within the treated timber ensures the durability of the fire performance in exterior exposure and severe damp situations. It is the only listed status type LR (leach resistant) treatment in the UK Wood Protection Association (WPA) Manual.

The durability of the reaction to fire performance after accelerated ageing in accordance with pr EN15912\* classifies NON-COM EXTERIOR treated timber as DRF Class EXT suitable for exterior conditions, coated or uncoated, as defined in Eurocode 5, EN1995-1-1 as Service Class 3 and in EN 335 as Use Class 3. The treated timber is non-hygroscopic – i.e. it does not absorb water from the air – nor does it give rise to efflorescence.

For further information, consult the Arch NON-COM EXTERIOR Environmental Aspects and Impact Information Sheet.

\*pr EN15912: the draft European Standard on Durability of Reaction to Fire Performance - Classes of fire retardant treated wood based product in interior and exterior end use applications.

## **DESIRED SERVICE LIFE**

NON-COM EXTERIOR functions primarily as a flame retardant and does not contain wood preservative chemicals. It does however, confer enhanced biological durability (EBD) to the treated timber. NON-COM EXTERIOR fire retardant treatment offers a 30 year desired service life to timber in Use Class 3 situations (as defined by EN335-1).

For further information, consult the Arch NON-COM EXTERIOR Environmental Aspects and Impact Information Sheet.

## **HEALTH, SAFETY, HANDLING AND DISPOSAL**

Reference should be made to the Consumer Information Sheet for NON-COM EXTERIOR fire retardant treated timber and sheet materials. This is available from the Arch Timber Protection Advisory Service. The Consumer Information Sheet is also relevant for COSHH purposes.

## FURTHER INFORMATION

Specifier's guide for NON-COM EXTERIOR fire retardant treated timber and sheet materials.

Consumer Information Sheet for NON-COM EXTERIOR fire retardant treated timber and sheet materials.

For further information please contact Arch Timber Protection using the contact details below.

*Arch Timber Protection Limited has produced this Code of Practice for information only. Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, Arch Timber Protection Limited gives no undertaking, warranty or promise that the information is correct and customers should take all reasonable precautions to ensure the use and application of NON-COM EXTERIOR fire retardant treated timber, as the case may be, is fit for the customers or end users particular purpose. Arch Timber Protection Limited expressly disclaims and excludes all warranties, conditions, representations and terms, whether expressed or implied by statute, common law or otherwise with respect to the information contained in this document or the subject matter thereof. Arch Timber Protection Limited reserves the right, at its sole discretion, to amend or withdraw any information contained in this document but does not undertake any duty to update such information.*

*This Code of Practice does not form part of any contract between Arch Timber Protection Limited and its customers and is not intended to give rise to any rights or cause of action for the customer against Arch Timber Protection Limited. This Code of Practice is for guidance only and the customer is advised to seek its own advice as to whether the products mentioned in the document are fit for the customer's particular purpose and are safe to use, store and handle in the circumstances contemplated by the customer. This Code of Practice does not negate any exclusions of liability of Arch Timber Protection Limited in the contract of sale for its products.*

*This Code of Practice has been written for businesses purchasing NON-COM EXTERIOR treated material from Arch Timber Protection Limited. The customer is advised to read the Code of Practice in full as it contains important information, but the customer needs to decide for itself whether or not the product is suitable for its or the end users particular purposes and should ensure that its employees, contractors and others working for it and who will use the products do so in a safe manner. This document is intended for use by businesses only and is not intended to be used by retail consumers.*



**Arch  
Timber  
Protection**

Wheldon Road, Castleford, West Yorkshire, WF10 2JT.  
Tel: (01977) 714000 Fax: (01977) 714001  
E-Mail: [advice@archchemicals.com](mailto:advice@archchemicals.com) [www.archtp.com](http://www.archtp.com)

IN CASE OF EMERGENCY TELEPHONE (0208) 762 8322 (24 hours).



BS EN ISO 9001:2000  
Reg No FM 1636



BS EN ISO 14001:2004  
Reg No EMS 539413



Responsible Care

© Copyright 2010 Arch Timber Protection.  
© Non-Com is a registered trademark of Arch Timber Protection.  
Arch Timber Protection updates its literature as and when necessary. Please ensure you have an up to date copy.